

MATERIALI

Principali norme di riferimento

MATERIALI

TUBI

RACCORDI

CALDARERIA

PREFABBRICAZIONI

Acciai inox

AISI Grade - Name	Main Trademarks ®	UNS	W.Nr.	EN	Density Kg/dm ³	PLATES	
						ASTM / ASME	EN
304	-	S30400	1.4301	X5CrNi18.10	8	A/SA 240	10028-7
304 L	-	S30403	1.4306	X2CrNi19.11	8	A/SA 240	10028-7
304 H	-	S30409	1.4948	X6CrNi18.10	8	A/SA 240	10028-7
321	-	S32100	1.4541	X6CrNiTi18.10	8	A/SA 240	10028-7
321 H	-	S32109	1.4878	X8CrNiTi18.10	8	A/SA 240	-
347	-	S34700	1.4550	X6CrNiNb18.10	8	A/SA 240	10028-7
347 H	-	S34709	1.4912	X8CrNiNb16.13	8	A/SA 240	10028-7
316	-	S31600	1.4401	X5CrNiMo17.12.2	8	A/SA 240	10028-7
316 L	-	S31603	1.4404	X2CrNiMo17.12.2	8	A/SA 240	10028-7
316LS	316 L Mod Urea	S31603	1.4435	X2CrNiMo18.14.3	8	A/SA 240	10028-7
316 H	-	S31609	1.4919	X6CrNiMo17.13	8	A/SA 240	-
316 Ti	-	S31635	1.4571	X6CrNiMo0Ti17.12.2	8	A/SA 240	10028-7
317 L	-	S31703	1.4438	X2CrNiMoN18.15.4	8	A/SA 240	10028-7
317 LN	-	S31753	1.4434	X2CrNiMoN18.12.4	8	A/SA 240	10028-7
317 LNM	-	S31726	1.4439	X2CrNiMoN17.13.5	8	A/SA 240	10028-7
309	-	S30900	1.4828	X15CrNiSi20.12	8	-	10095
309 S	-	S30908	1.4833	X12CrNi 23-13	8	A/SA 240	-
310 S	-	S31008	1.4845	X12CrNi25.21	8	A/SA 240	-
310 MoLN	25.22.2 Urea	S31050	1.4466	X1CrNiMoN25.22.2	8	A/SA 240	10028-7
310 L NAG	URANUS 65	S31002	1.4335	X1CrNi25.21	7.9	-	10028-7
330	Incoloy 330	N08330	1.4864	-	8	B/SB 536	-
S1	URANUS S1- A610	S30600	1.4361	X1CrNiSi18.15.4	8	A/SA 240	-
904 L	URANUS B6 - 2RK65	N08904	1.4539	X1NiCrMoCu25.20.5	8	A/SA 240	10028-7
926 - 6Mo	-	N08926	1.4529	X1NiCrMoCuN25.20.7	8	B/SB 625	10028-7
6 Mo	254SMO	S31254	1.4547	X1CrNiMoCuN20.18.7	8	A/SA 240	10028-7
6 Mo	AL6XN	N08367	-	-	8	A/SA 240 - B/SB688	-
-	253MA	S30815	1.4835	X10CrNiSiN21.11	8	A/SA 240	-
Alloy 28	SANICRO 28	N08028	1.4563	X1NiCrMoCu31.27.4	8	B/SB 709	10028-7
Alloy 31	-	N08031	1.4562	X1NiCrMoCu32.28.7	8.1	B/SB 625	-
Alloy 33	-	R20033	1.4591	X1CrNiMoCuN33.32.1	7.9	B/SB 625	-
Lean Duplex 2101	LDX 2101	S32101	1.4162	X2CrMnNiN22-5-2	7.8	A/SA 240	-
Duplex 2304	URANUS 35N	S32304	1.4362	X2CrNiN23.4	7.8	A/SA 240	10028-7
Duplex 2205	SAF 2205 - URANUS 45N	S32205 - S31803	1.4462	X2CrNiMoN22.5.3	7.8	A/SA 240	10028-7
Superduplex 2507	SAF 2507 - URANUS 47N	S32750	1.4410	X2CrNiMoN25.7.4	7.9	A/SA 240	10028-7
Superduplex	ZERON 100	S32760	1.4501	X2CrNiMoCuWN25.7.4	7.9	A/SA 240	10028-7
Superduplex	URANUS 52 N	S32550 - S32520	1.4507	X2 Cr Ni Mo Cu N 25.6.3	8	A/SA 240	10028-7

© Informazioni sui marchi registrati:

Alcuni sono nomi commerciali o marchi di produttori specifici. Officine Orsi non è affiliato ad alcun produttore. I nomi sono elencati solo per riferimento e per aiutare ad identificare i prodotti con le specifiche indicate.

- A610 è un marchio del gruppo Böhler Uddeholm.
- Zeron 100 è un marchio di Weir Materials Ltd.
- Uranus è un marchio del gruppo Arcelor-Mittal.
- 2RK 65, Sanicro 28 e SAF sono marchi registrati di Sandvik AB.
- 253 MA, 254 SMO e LDX 2101 sono marchi del gruppo Outokumpu.
- AL6XN è un marchio di Allegheny Ludlum.

Stainless steels

	WELDED PIPES		SEAMLESS PIPES		FITTINGS		VdTÜV
	ASTM / ASME	EN	ASTM / ASME	EN	ASTM / ASME	EN	
	A/SA 312 – A/SA 358	10217-7	A/SA 312	10216-5	A/SA 403	10253-4	411
	A/SA 312 – A/SA 358	10217-7	A/SA 312	10216-5	A/SA 403	10253-4	411
	A/SA 312 – A/SA 358	-	A/SA 312	10216-5	A/SA 403	-	-
	A/SA 312 – A/SA 358	10217-7	A/SA 312	10216-5	A/SA 403	10253-4	411-454
	A/SA 312	-	A/SA 312	-	A/SA 403	-	-
	A/SA 312 – A/SA 358	10217-7	A/SA 312	10216-5	A/SA 403	10253-4	-
	A/SA 312	-	A/SA 312	-	A/SA 403	-	-
	A/SA 312 – A/SA 358	10217-7	A/SA 312	10216-5	A/SA 403	10253-4	411
	A/SA 312 – A/SA 358	10217-7	A/SA 312	10216-5	A/SA 403	10253-4	411
	A/SA 312 – A/SA 358	10217-7	A/SA 312	10216-5	A/SA 403	10253-4	411
	A/SA 312 – A/SA 358	-	A/SA 312	-	A/SA 403	-	-
	A/SA 312	10217-7	A/SA 312	10216-5	A/SA 403	10253-4	454
	A/SA 312	10217-7	A/SA 312	-	A/SA 403	10253-4	-
	A/SA 312	-	A/SA 312	10216-5	A/SA 403	-	-
	A/SA 312 – A/SA 358	10217-7	A/SA 312	-	A/SA 403	10253-4	405
	-	10296-2	-	-	-	-	-
	A/SA 312 – A/SA 358	-	A/SA 312	-	A/SA 403	-	-
	A/SA 312 – A/SA 358	-	A/SA 312	-	A/SA 403	-	541
	A/SA 312	-	A/SA 312	10216-5	-	-	415
	A/SA 312	-	A/SA 312	10216-5	-	10253-4	468
	B546	-	B/SB 535	-	B/SB 366 WP330	-	-
	A/SA 312 – A/SA 358	-	A/SA 312	-	-	-	-
	A/SA 312 – A/SA 358	10217-7	A/SA 312	10216-5	A/SA 403	10253-4	421
	B/SB 673 – A/SA 312 – B/SB 804	10217-7	B/SB 677	10216-5	B/SB 366	10253-4	502
	A/SA 312 – A/SA 358	10217-7	A/SA 312	10216-5	A/SA 403	10253-4	473
	B/SB 675 – A/SA 312 – B/SB 804	-	A/SA 312	-	B/SB 366	-	-
	A/SA 312 – A/SA 358	-	A/SA 312	-	-	-	-
	-	10217-7	B/SB 668	10216-5	-	10253-4	483
	B/SB 619	-	B/SB 622	-	B/SB 366 WP3127	-	509
	B/SB 619	-	B/SB 622	-	-	-	516
	A/SA 790 – A 928	-	A/SA790	-	A/SA 815	-	-
	A/SA 790 – A 928	10217-7	A/SA790	10216-5	-	10253-4	496
	A/SA 790 – A 928	10217-7	A/SA790	10216-5	A/SA 815	10253-4	418
	A/SA 790 – A 928	10217-7	A/SA790	10216-5	A/SA 815	10253-4	-
	A/SA 790 – A 928	10217-7	A/SA790	10216-5	A/SA 815	10253-4	-
	A/SA 790 – A 928	-	A/SA 790 – A 928	10216-5	A/SA 815	10253-4	-

© Registered Trademark information :

Some names are trade names or trademarks of specific manufacturers. Officine Orsi is not affiliated with any manufacturer. Names are listed only for reference in order to help to identify products with their indicated specifications.

- A610 is a trademark of the Böhler-Uddeholm.
- Zeron 100 is a trademark of Weir Materials Ltd.
- Uranus is a trademark of the Arcelor-Mittal.
- 2RK 65, Sanicro 28 and SAF are trademarks of Sandvik AB.
- 253 MA, 254 SMO and LDX 2101 are trademarks of Outokumpu.
- AL6XN is a trademark of Allegheny Ludlum.